

## Gloss White PE.85um/AS400/62g White Glassine

### Facestock : Gloss White PE.85um

		UNITS	VALUE	TOLERANCE
Caliper	Average Value	um	83	±2
Caliper	Limit Value	um	74-90	
Weight		Gsm <sup>2</sup>	78	±5
Opacity			85-100	
Intensity of Corona		dyn	42	
Tensile Strength MD		mpa	18-26	
Tensile Strength CD		mpa	17-25	
Elongation MD	At break		500-900	
Elongation CD			500-900	
Haze			25-33	

### Adhesive : Adhesive AS400

Permanent Acrylic base adhesive. Stable and easy for waste discharge.

		UNITS	VALUE	TOLERANCE
Weight		gsm	20	±2
Tack	FTM9	N	9.73	
Shear	FTM8	h	24	
Peel Adhes 180°	FTM1	KN/m or N	5.77	
Min Application Temp		°C	8	
Suitable Temp		°C	-50 — +90	

### Liner : 62g White Glassine Paper

Super calendared glassine liner. Primarily used for roll-to-roll label conversion and photo electric detection labelling system.

		UNITS	VALUE	TOLERANCE
Weight	ISO536	gsm <sup>2</sup>	60	±3
Caliper	ISO534	um	55	±5
Transparency	DIN53147	%	49	±3
Master Width	m		1530	

## Application

This product is suitable for a wide range of promotional and industrial label applications.

Especially for personal care, cosmetics and oil barrel labelling.

Test if labelling on rough surfaces.

Polypropylene materials can be reused.

## Storage

Two years when stored at 20°C at 50% RH. Avoid direct sunlight and keep storage environment dry and ventilated.

***All pressure sensitive materials are sold with the understanding that the purchaser has tested and assessed the material is suitable for the task***

